

Technical Data Sheet TDS 005 — Landscape Paving Guidelines

LANDSCAPE PAVING GUIDELINES

Description

SOILBOND A01 stabiliser / binder is a naturally derived water-based organic emulsion used for the stabilisation of granitic sand based pavement materials.

Key properties include:

- Increased cohesion
- Reduced water sensitivity; and
- Improved wet strength

Granitic sand in these guidelines covers all varieties of finely graded granitic based crushed rocks and gravel including decomposed granite used for landscape paving purposes.

Product Safety

SOILBOND A01 stabiliser / binder is classified Non-Hazardous and Non Dangerous Goods. This means it is safe for handling, storage and transportation. As with all products, please refer to the Material Safety Data Sheet before use.

Applications

Wearing course stabilisation with the SOILBOND A01 stabiliser / binder is used to:

- Increase cohesion of granitic sand;
- Provide reduced moisture susceptibility;
- Improve pavement material strength;
- Bind the fine particles to improve dust control; and
- Reduce the problems associated with materials that deform and shove when subjected to traffic.

Note: Dilute One Part SOILBOND A01 stabiliser / binder with One Part water prior to mixing.

The advantages of SOILBOND A01 bound wearing courses may be in the following applications:

- Pedestrian or cycle trafficked pavements susceptible to mechanical erosion;
- Areas subjected to flooding or rain erosion;
- Dust control improvements for pavements in sensitive areas;
- Improving the load carrying capacity of a pavement; and
- Where life cycle costs can be minimised as an alternative to regular maintenance schedules.

Mix Design

The table below indicates the range of application rates and treatment depths to calculate the mix design. Individual mix design will be dependent on the site conditions, material properties, pavement gradient and traffic type and volume.

Treatment Depth in mm	SOILBOND A01 Rate % of Dry Weight of Material*		
	2%	3%	4%
	Usage Rate in kg/m ²		
50	2	3	4
75	3	4.5	6

* Based on a compacted density of 2 tonnes per m³.

Technical Data Sheet TDS 005 — Landscape Paving Guidelines

LANDSCAPE PAVING GUIDELINES

Note: Dilute One Part SOILBOND A01 stabiliser / binder with One Part water prior to mixing.

Construction - NEW Paths or Tracks

(A) Onsite Stockpile Mixing using a Bobcat

Applying SOILBOND A01 stabiliser / binder to stockpile and mixing

- Step 1: The stockpile is flattened and some SOILBOND is sprayed onto the surface.
- Step 2: Mixing using the bobcat.
- Step 3: As the granitic sand is turned over further SOILBOND is added to the turned over material and the stockpile.
- Step 4: Mixing continues.
- Step 5: Turning over the material mixing in SOILBOND .
- Step 6: The required amount of SOILBOND is added gradually whilst mixing occurs.
- Step 7: Once all the required SOILBOND is added to the stockpile, mixing continues to ensure uniform distribution.

Continue mixing until the binder has consistently coated the material and uniform colour is achieved.

(B) Off Site Mixing using a Pug Mill at Quarry

Pug Mill Stabilisation

Usually performed at the quarry, the granitic sand is loaded into storage bins. The material is then conveyed to a Pug Mill mixer, where the SOILBOND A01 stabiliser / binder is added and uniformly mixed in the same stage. Moisture content levels are also adjusted at this stage. When mixing is complete the mixed material is transported in trucks to the site of installation.

Construction - EXISTING Paths or Tracks

Onsite Stabilisation - Existing Paths or Tracks

Insitu Stabilisation

The following description is for a multiple pass mixing process. Multiple passes ensure good uniformity of mixing.

The general construction process is:

- Step 1: Rip the pavement to the recommended depth. If necessary, new granitic sand is added at this stage.
- Step 2: Apply water to assist incorporation of the SOILBOND A01 binder and obtain the required moisture content for compaction.
- Step 3: Apply binder at the recommended spread rate followed by mixing.
- Step 4: Mechanically mix the binder into the ripped material. Mixing equipment will depend on the area size: grader, tractor mounted rotary hoe, road profiler, skid steer with appropriate attachment or hand rotary hoe.
- Step 5: Continue application and mixing until the binder has consistently coated the material. Use the "hand clench/snowball" test to confirm suitable binding and moisture content prior to compaction.
- Step 6: When material is sufficiently mixed, levels should be adjusted and shaping of the pavement completed prior to compaction.
- Step 7: Compact with a steel smooth drum roller, vibrating roller / vibrating plate until a smoothly graded finish is obtained.
- Step 8: The stabilised pavement undergoes conditioning and curing process.
- Step 9: Care must be taken to treat and well compact the material adjacent to the edges to prevent erosion to occur at edges.

Technical Data Sheet TDS 005 — Landscape Paving Guidelines

LANDSCAPE PAVING GUIDELINES

Construction - NEW Paths or Tracks (*continued*)

Optimum Moisture Content (OMC)

Off site mixing of granitic sand with a Pug Mill, and transporting to the construction site for installation can result in drying out of the granitic sand. It is important to ensure that prior to compaction the mixed material has the Optimum Moisture Content.

Quality Management

Quality management is essential to produce a material that will provide the desired performance in the field. To control quality the following factors should be considered:

- Uniformity of the material to be stabilised;
- Quantity and uniformity of distribution of the SOILBOND A01 stabiliser / binder;
- Thickness (and uniformity of thickness) of the stabilised layer;
- Quality of mixing;
- Compacted density; and
- Surface finish.

Construction - EXISTING Paths or Tracks (*continued*)

Optimum Moisture Content (OMC)

When applying SOILBOND A01 stabiliser / binder insitu it is important to ensure that prior to compaction the mixed material has the Optimum Moisture Content. Use the "hand clench/snowball" test to confirm suitable binding and moisture content.

Quality Management

Quality management is essential to produce a material that will provide the desired performance in the field. To control quality the following factors should be considered:

- Uniformity of the material to be stabilised;
- Quantity and uniformity of distribution of the SOILBOND A01 stabiliser / binder;
- Thickness (and uniformity of thickness) of the stabilised layer;
- Quality of mixing;
- Compacted density; and
- Surface finish.